



# FlexFoam-iT! Series

Flexible Polyurethane Foams

## PRODUCT OVERVIEW

FlexFoam-iT! III, FlexFoam-iT! V and FlexFoam-iT! X are two-component flexible foams that are versatile and easy to use. Parts A + B are mixed and poured into a mold or other form (apply release agent if necessary). FlexFoam-iT! III is mixed 1A:2B by volume, expands 15 times its original volume and develops a uniform 3 lb./cu. ft. cell structure. FlexFoam-iT! V is mixed one to one by volume and expands 10 times its original volume and develops a uniform 5 lb./cu. ft. cell structure. FlexFoam-iT! X is mixed one to one by volume and expands 6 times its original volume and develops a uniform 10 lb./cu. ft. cell structure. Foam expands to full volume in 5 minutes, develops handling strength in 30 minutes and fully cures in two hours. Vibrant colors can be achieved by adding color pigments.

Flex-Foam-It! Products can be used for a variety of arts & crafts, industrial and special effects applications including padding/cushion material, gasket material and scenic design.

## TECHNICAL OVERVIEW

- Key Values:**
- ~Color: White
  - ~Handling Strength: 30 Minutes
  - ~Full Cure: 2 Hours
  - ~Mixing Ratios:
    - FlexFoam-iT! III: 1A:2B by volume (57.5A : 100B by weight)
    - FlexFoam-iT! V & X: One to One by volume. (105A:100B by weight)
  - ~Pot Life:
    - FlexFoam-iT! III: 35 seconds
    - FlexFoam-iT! V & X: 1 Minute

COMPONENTS	COLOR	VISCOSITY	S.G. g/cm <sup>3</sup>	S.V. cu. in./lb.	Lbs./Cu Ft=Kg/Cu Meter
Mixed Part A + B	White	1,000 cps			
FlexFoam-iT! III			0.06	400-450	3 lb/ft <sup>3</sup> = 48 kg/m <sup>3</sup>
FlexFoam-iT! V			0.1	275-300	5 lb/ft <sup>3</sup> = 80 kg/m <sup>3</sup>
FlexFoam-iT! X			0.18	150-200	10 lb/ft <sup>3</sup> =160 kg/m <sup>3</sup>

### Applying A Release Agent                      Mixing                      Pouring

**Preparation . . .** Materials should be stored and used in a warm environment (72° F / 23° C). Mixing tools and containers should be clean and made of metal, glass or plastic. **Mixing should be done in a well-ventilated area.** Wearing eye protection, latex gloves and long-sleeve garments to minimize skin contact is strongly recommended. Some surfaces must be sealed.

**Applying A Release Agent . . .** A release agent is necessary to facilitate demolding when casting into or over most surfaces. Use a release agent made specifically for releasing urethane foams such as

**Ease Release 2831** available from Smooth-On or your Smooth-On distributor. Do not use a silicone based release agent. A liberal coat of release agent should be applied onto all surfaces that will contact the foam. **~IMPORTANT:** To ensure thorough coverage, lightly brush the release agent with a soft brush over all surfaces. Let the release agent dry for 30 minutes.

**Mixing . . .** After dispensing equal amounts of Parts A and B into mixing container, mix thoroughly for 45 seconds. Stir quickly and deliberately, making sure you scrape the sides and bottom of the mixing container several times. Be careful not to splash low-viscosity material out of the container. **Remember, this product cures quickly.** Do not delay between mixing and pouring.

**Pouring . . .** For best results, pour your mixture in a single spot at the lowest point of the containment field and let the mixture seek its level.

**IMPORTANT:** Shelf life of product is drastically reduced after opening. Remaining product should be used as soon as possible. Immediately replacing the lids on both containers after dispensing product will help prolong the shelf life of the unused product. **XTEND-IT Dry Gas Blanket** (available from Smooth-On) will significantly prolong the shelf life (up to 4 times longer) of unused liquid urethane products.

***Safety First!***

***Safety First!***

***Safety First!***

The material safety data sheet (MSDS) for this or any Smooth-On product should be read before using and is available on request. All Smooth-On products are safe to use if directions are read and followed carefully. **Keep Out Of Reach Of Children!**

***Be careful.*** Part A (Yellow Label) contains methylene diphenyldiisocyanate. Vapors, which can be significant if heated or sprayed, may cause lung damage and sensitization. Use only with adequate ventilation. Contact with skin and eyes may cause severe irritation. Flush eyes with water for 15 minutes and get immediate medical attention. Remove from skin with soap and water. Part B (Blue Label) is irritating to the eyes and skin. Avoid prolonged or repeated skin contact. If contaminated, flush eyes with water for 15 minutes and get immediate medical attention. Remove from skin with soap and water. When mixing with Part A, follow precautions for handling isocyanates. If machining cured FlexFoam-It!, wear dust mask or other apparatus to prevent inhalation of residual particles.

***Important*** - The information contained in this bulletin is considered accurate. However, no warranty is expressed or implied regarding the accuracy of the data, the results to be obtained from the use thereof, or that any such use will not infringe a copyright or patent. User shall determine suitability of the product for the intended application and assume all associated risks and liability.

***Call Us Anytime With Questions About Your Application.***

Phone: (212) 367-7561

Fax: (212) 243-6374

Visit Us At Our Website: [www.SCULPT.com](http://www.SCULPT.com)

Ask About Urethane and Silicone Moldmaking Products.