



THE COMPLEAT SCULPTOR

90 Vandam Street New York NY 10013
212-243-6074 TCS@SCULPT.com
800-9-SCULPT www.SCULPT.com

TECHNICAL INFORMATION SHEET - P-44 Silicone Rubber

Description

P-44 silicone rubber is a translucent two-component, addition reaction, platinum catalyzed system that cures at room temperature. It has a moderate durometer, superb physical properties, excellent release and good chemical resistance. There are two activators available: P-44 A used for casting pigmented parts, and P-44 A Option 2 used for casting clear polyurethanes.

Applications

P-44 is used to make molds where visual inspection is required. The combination of physical integrity and moderate hardness make it an excellent choice for prototyping. Due to its flexibility and ease in releasing, it performs well with expandable foam systems, maintaining its shape and detail for multiple castings.

Mixing Instructions

Mix 100 parts by weight of P-44 Base with 10 parts by weight of P-44 Activator in a container that will hold approximately 4 to 5 times the volume being used. Stir thoroughly either by hand or by mechanical mixing. Immediately after mixing, place the material in a vacuum chamber capable of 28 to 29 inches of mercury vacuum. The material will expand to approximately quadruple its original volume and then collapse. Maintain the vacuum for an additional 2 to 3 minutes and then remove. Carefully pour the catalyzed silicone rubber over the released pattern (MR-15 is recommended).

Curing

Vulcanization of the P-44 takes place in 18 to 24 hours after mixing at normal room temperatures (70°F to 75°F). Heat can be used to accelerate the cure rate. Care must be taken to ensure that the master doesn't gas or give off vapors at the temperature used, since this can cause severe distortion of the mold surface. Some woods give off moisture and gas at relatively low temperatures causing failure in the mold making attempt.

Average cure times for one-half inch thick samples are listed below:

Temperature	70°F	90°F	125°F	150°F	200°F	250°F	300°F
Cure Time	18 to 24 hours	3.5 hours	1.5 hours	45 minutes	25 minutes	15 minutes	10 minutes

The P-44 has a long room temperature work time, but the application of heat will cause this time to shorten. Cure rates can be accelerated at room temperature using Pt Accelerator (refer to Pt Accelerator data sheet for details). Heat accelerated cures and Pt Accelerator will cause some shrinkage and a slight decrease in the physical properties.

Cure Sensitivity

P-44 may have its cure inhibited at the interface between the mold and the master. Models that have come in contact with tin catalyzed rubbers (the GI-Series) may show cure inhibition at the face of the mold. This can usually be prevented by thoroughly cleaning the model with naphtha or methylene chloride, releasing and checking the area by brushing on a small amount of catalyzed P-44 rubber. After 24 hours this film must be cured and non-sticky. In the event that the contamination still exists, the model should be cleaned again and a thin film of acrylic or nitrocellulose lacquer or base coat should be applied. This should serve as a barrier coat and allow a completely cured mold to be prepared. Other substrates such as clay containing sulfur or any other sulfur, amine, or tin contaminated materials will cause surface inhibition and in all cases a test should be run as outlined above to determine compatibility.

Typical Properties

Color of Base	Translucent	Tear strength, ppi	120 ± 20
Color of Activator	Clear	Tensile strength, psi	600 ± 50
Viscosity, base, cps	100,000	Elongation, %	250 ± 25
Viscosity, mixed, cps	50,000 ± 10,000	Shrinkage, %	Nil
Specific gravity	1.08	Shelf Life(months)	6
Working time, hours	1 to 2		
Shore A hardness	45 ± 3		

The information contained in this product information sheet is based on sources believed to be accurate. It is offered in good faith, but without guarantee since the conditions of use are beyond our control. All risks of use are assumed by the user.

Technical Support: (212) 367-7561
www.SCULPT.com