



THE COMPLEAT SCULPTOR

90 Vandam Street New York NY 10013

212-243-6074 TCS@SCULPT.com

800-9-SCULPT www.SCULPT.com

TECHNICAL INFORMATION SHEET - P-70 SILICONE RUBBER

DESCRIPTION

P-70 is a two component addition cure silicone rubber mold making material. It has the high durometer necessary for use in the pottery and ceramics industry, and exhibits negligible shrinkage, giving it the dimensional stability needed for prototype making. P-70 cures at room temperature in 18 to 24 hours; however, the curing rate can be accelerated with Pt Accelerator at room temperature or with heat.

MIXING INSTRUCTIONS

Mix 10 parts by weight of P-70 base with 1 part by weight of P-70 activator in a container that will hold about three times the volume of the rubber being mixed. Stir thoroughly either by hand or by mechanical means until a uniform green color is achieved. Immediately after mixing, place the container in a vacuum chamber capable of 28 inches of mercury vacuum. The rubber will expand to double or triple its original volume as it is being deaired. After the rubber collapses, maintain the vacuum for an additional two minutes and then release. Carefully pour the catalyzed silicone rubber over the released pattern (MR-15 is recommended).

TYPICAL PROPERTIES

Color, Base	Tan
Color, Activator	Green
Base viscosity (cps)	140,000 - 160,000
Activator viscosity (cps)	1,500 - 2,500
Working Time (hrs)	1 - 2
Cure Time (hrs)	18 - 24
Specific Gravity, cured rubber	1.36
Shore A Hardness	
24 hours @ 70oF/50% R.H.	60 ± 3
+ 2 hours @ 250oF	70 ± 3
Tear Resistance (ppi)	85 ± 10
Tensile Strength (psi)	775 ± 50
Elongation (%)	150 ± 25
Shrinkage (%)	nil

The information contained in this product information sheet is based on sources believed to be accurate. It is offered in good faith, but without guarantee since the conditions of use are beyond our control. All risks of use are assumed by the user.

Technical Information Hotline (212) 367-7561

www.SCULPT.com